



# VAPOR LOCK™ 20/20

Accreditations: ASTM C494 | NSF - 61

## DESCRIPTION

Vapor Lock™ 20/20 is a ready to use concrete admixture that when properly utilized makes concrete water and vapor proof. Vapor Lock™ 20/20 reacts with the calcium hydroxide created by the Portland cement reaction with water. This chemical reaction is similar to a pozzolanic material such as flyash, GGBFS and silica fume, but more controlled and predictable.

## BASIC USES

Vapor Lock™ 20/20 is used in applications where it is desirable to bond moisture sensitive coatings and adhesives to any concrete surface including flooring, roofing, fluid applied air barriers, or below grade water proofing.

## MAJOR ADVANTAGES OF VAPOR LOCK™ 20/20

- Allows for the installation of moisture sensitive coatings & adhesives within the construction schedule
- Warranted labor & material replacement in the event of a moisture related failure
- Provides a comprehensive risk management tool for all stakeholders
- Warranty is underwritten by Lloyd's of London for each project with a 3rd party insurance policy
- No topical moisture treatments are necessary
- Tremendous cost & schedule savings
- Increased concrete density & hardness
- Increased abrasion resistance
- Virtually eliminates:
  - » Dusting
  - » Slab curl
  - » Plastic & drying shrinkage cracking
  - » Freeze-thaw spalling
  - » De lamination

## TECHNICAL & PRODUCT DATA

Appearance:	Clear
Odor:	None
Toxicity:	None
Flammability:	None
pH:	11-12
Shelf Life:	1 Year
Weight:	5Kg per 3.8 Litres
Freeze Temp:	0°C
Storage Temp:	1.6°C - 24°C
Solvent:	None, water based
Acid	
Resistance:	Excellent
Hazardous	
Vapors:	None
Capillary	
Break:	Integral C-S-H
Installation:	All cementitious materials
Number of components:	1
Packaging:	1320L Totes, 1040L Totes, 208L Drums, 20L Containers



SPECIALTY  
PRODUCTS  
GROUP

# VAPOR LOCK™ 20/20

Accreditations: ASTM C494 | NSF - 61

## APPLICATION INSTRUCTIONS

Cast in Place, Normal Weight Concrete - Vapor Lock 20/20™ standard dosage is 10 ounces per 100 weight of cementitious materials and should be added with the head water for the best results. Contact your SPG representative for dosage rate verification or if introduction with the head water is not possible or practical. This dose needs to be accurate within 0% and +3%. Vapor Lock™ 20/20 must be added to concrete by a ready mix or pre-cast provider that is certified by SPG to utilize this material.

## SPECIAL HANDLING

Do not allow the product to freeze. Discard any frozen or separated product.

## SAFETY

Please refer to SDS at [spggogreen.com.au](http://spggogreen.com.au) or contact SPG.

## PROJECT SPECIFIC WARRANTY

Project specific Warranties are available for water proofing and spalling elimination. These Warranties must be pre-approved by manufacturer and contain certain limitations.

All SPG warranties are underwritten by a Lloyd's of London policy in the amount of CAD\$20,000,000.00. For more information, contact your SPG representative.

## WARRANTY DISCLAIMER

The information herein is to assist customers with product selection. Our products are intended for sale to qualified industrial and commercial customers. Customers shall be responsible for inspection of product prior to use to determine suitability for and applicability to their application. Trial batch mixes are encouraged with certified ready mix providers. We warrant that our products will meet our written specifications. Nothing herein shall constitute a warranty expressed or implied, including any warranty of merchantability or fitness, nor is protection from any loss or patent to be inferred. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special, incidental or consequential damages. Project specific warranties are available for waterproofing and concrete durability.

Contact SPG prior to installation for project specific warranty registration and requirements.